


Demagnetization Curves



| RE2Co17 (222/199) | | 单位 Units | 最大值 Max | 最小值 Min | 典型值 Typical values |
|--|--|-------------|------------|------------|-----------------------|
| 磁性参数 Magnetic parameters | 剩磁 Br Residual Induction | KGs | 11.1 | 10.8 | 11 |
| | | T | 1.11 | 1.08 | 1.1 |
| | 磁感应矫顽力.HcB Coercivity | KOe | | 9.9 | |
| | | KA/m | | 788 | |
| | 内禀矫顽力.HcJ Intrinsic Coercivity | KOe | | 25 | |
| | | KA/m | | 1990 | |
| | 最大磁能积.(BH) max Maximum Energy Product | MGOe | 31 | 28 | 29 |
| KJ/m ³ | | 247 | 222 | 231 | |
| 剩磁温度系数 α (Br) of Induction, α(Br) | %/°C | | -0.035 | | |
| 矫顽力温度系数 α (Hcj) of Coercivity, α(Hcj) | %/°C | | -0.2 | | |

| RE2Co17 (222/199) | | 单位 Units | 平行于磁化方向 C// | 垂直于磁化方向 C⊥ |
|--|--|-------------------|----------------|---------------|
| 机械物理性能参数 Mechanical and physical performance parameters | 热膨胀系数 (20~200°C) Coefficient of Thermal Expansion | E-6/K | 7~9 | 10~13 |
| | 工作温度 Working temperature | °C | | 350 |
| | 居里温度 Curie Temperature, Tc | °C | | 820 |
| | 抗弯强度 Flexural Strength | Mpa | | 100 |
| | 抗压强度 Compressive Strength | Mpa | | 700 |
| | 杨氏模量 Young's Modulus | Gpa | | 2.4 |
| | 密度 Density | g/cm ³ | | 8.3~8.5 |
| | 维氏硬度 Hardness, Vickers | Hv | | 550 |

- 注: 1、客户有特殊要求, 按客户要求。居里温度、温度系数只作为参考依据, 不作为判定依据。
 Curie temperature and temperature coefficient are for reference only, but not as inspection base.
- 2、上面所示的材料数据和退磁曲线代表典型的属性, 由于产品形状和大小可能不同。
 The material data and demagnetization curves shown above represent typical properties that may vary due to product shape and size.
- 3、用户对磁体的磁性能有特殊要求的, 由供需双方商定的技术协议执行。
 The user can have a special requirement on the magnets, magnetic, performed by the supply and demand both sides agreed on the technical agreement.